



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)


(51) International Patent Classification <sup>7</sup> : <b>A61F 13/15</b>		A1	(11) International Publication Number: <b>WO 00/56257</b>
			(43) International Publication Date: 28 September 2000 (28.09.00)
(21) International Application Number: PCT/US00/07324 (22) International Filing Date: 20 March 2000 (20.03.00) (30) Priority Data: 09/272,119          19 March 1999 (19.03.99)          US (71) Applicant: KIMBERLY-CLARK WORLDWIDE, INC. [US/US]; 401 N. Lake Street, Neenah, WI 54956 (US). (72) Inventors: KUGLER, Joseph, Michael; N1453 Wildwood Drive, Greenville, WI 54942 (US). VENTURINO, Michael, Barth; 2124 Omega Drive, Appleton, WI 54915 (US). (74) Agents: CURTIN, Jeffrey, B. et al.; Kimberly-Clark World- wide, Inc., 401 N. Lake St., Neenah, WI 54956 (US).		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).  Published <i>With international search report.          Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>	

(54) Title: METHOD AND APPARATUS FOR FORMING AN APERTURED PAD

## (57) Abstract

An apparatus and method for manufacturing a pad (24) wherein a rotatable forming screen (22) which has a generally cylindrical surface and at least one outwardly projecting nob (50) is employed. The nob (50) is positioned on the forming screen (22) whereby the nob (50) is circumscribed by the material, e.g., cellulosic fluff, deposited on the forming screen to form the pad (24). The pad (24) is transferred from the forming screen (22) to a moveable transfer surface (34). The transfer surface (34) may be either flat or round and moves at a velocity which is at least as great as the velocity of the forming screen. The nob (50) located on the forming screen includes a thrust surface disposed on a trailing edge (66) of the nob (50). The thrust

surface imparts a compressive force on the pad during the release of the pad (24) from the forming screen (22). The compressive force is at least partially directed towards the transfer surface (34) and thereby assists in the release and transfer of the pad (24).



*FOR THE PURPOSES OF INFORMATION ONLY*

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
BF	Burkina Faso	GR	Greece		Republic of Macedonia	TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

## METHOD AND APPARATUS FOR FORMING AN APERTURED PAD

Background of the Invention

The present invention relates to the apparatus and methods used to form  
5   apertured pads. More specifically, the present invention relates to apparatus and  
methods used to form absorbent apertured pads which may be used in such products as  
disposable diapers, training pants, incontinence garments, catamenial products and other  
absorbent articles.

Conventional absorbent pads often consist primarily of a cellulosic fluff or other  
10   fibrous material. Such absorbent pads may be used in the manufacture of products  
subject to surge loadings. The expected surge loadings may exceed the rapid intake  
capability of conventional absorbent pads. Apertures placed in the pads, however, can  
enhance the rapid intake capability of the pad. Such apertures may consist of empty  
voids or be filled with a material having different properties than the remainder of the pad.

15   Such apertures may be employed for purposes other than enhancing the rapid  
intake capability of the pad. For example, when the apertured pad is used in a disposable  
diaper, the apertures may provide additional void space for storing and receiving solid  
wastes or to provide space for the expansion of superabsorbent materials.

The conventional manufacture of apertured pads involves air laying a fluff pad on a  
20   forming drum. The pad is subsequently apertured in a separate cutting, calendering or  
similar procedure. U.S. Patent No. 5,242,435 discloses, *inter alia*, the calendering and  
perforating of a cellulosic pulp fluff sheet. U.S. Patent No. 5,785,697 discloses a  
different method of forming an apertured pad which involves, *inter alia*, the use of raised  
portions on a forming surface employed to form an absorbent composite web.

25

Summary of the Invention

The present inventors have recognized difficulties and problems inherent in the  
prior art and in response thereto have developed an improved apparatus and method for  
30   forming an apertured pad.

In one aspect, the present invention provides an apparatus for manufacturing a  
pad wherein the apparatus comprises, *i.e.*, includes but is not limited to, a rotatable  
forming screen which has a generally cylindrical surface and at least one outwardly  
projecting nob. The nob is located on the screen in a position whereby the nob is  
35   circumscribed by the forming screen. The forming screen is rotatable at a rate which  
defines a first tangential velocity of the screen. A material source is positioned adjacent

the forming screen whereby a material layer may be air layed on the forming screen and the nob may be circumscribed by the material layer. The deposited material layer has a first surface in contact with the forming screen and an opposite second surface. A moveable transfer surface is engageable with the second surface of the material layer.

- 5 The transfer surface is moveable in a direction which substantially corresponds to the movement of the material layer and at a second velocity which is at least as great as the first tangential velocity of the forming screen. The apparatus also includes a means for attracting the material layer to the transfer surface which may, in some embodiments, be a vacuum source disposed in operative communication with the transfer surface. The nob  
10 located on the forming screen includes a thrust surface disposed on a trailing edge of the nob. The thrust surface imparts a compressive force on the material layer at the point where the material layer is engageable with the transfer surface and as the forming screen and the transfer surface move at their respective first and second velocities. The compressive force exerted by the thrust surface of the nob includes a component vector  
15 which is directed towards the transfer surface.

In some embodiments of the apparatus, the velocity of the transfer surface may be 101, 102, 103, or a greater percentage of the tangential velocity of the forming screen at the transfer location.

- 20 In other embodiments of the apparatus, the transfer surface may be either a flat surface or a substantially cylindrical surface. In those embodiments wherein the transfer surface is a substantially cylindrical surface, the forming screen can have a radius which is less than, approximately equivalent to, or larger than the radius which defines the transfer surface. When the forming screen has a larger radius, the forming screen radius may be greater than twice or three times the magnitude of the transfer surface radius.

- 25 The nob disposed on the forming screen can have many different shapes. The nob may have sidewalls which incline inwardly by about 5° to form an angle of approximately 85° with the forming screen. Such nobs may have a shape which defines a frustum.

- The apparatus may also include a plurality of nobs located on the forming screen.  
30 The nobs may also be reattachable to the screen as, for example, by using threaded fasteners to secure the nobs to the forming screen. The use of reattachable nobs allows the nobs on the forming screen to be exchanged in a relatively convenient manner.

- The present invention also provides a method of forming an apertured pad. One such method includes providing a forming screen with at least one outwardly projecting  
35 nob and rotating the forming screen whereby the screen has a first tangential velocity. A

pad is formed on the forming screen whereby the pad completely encircles the nob. The pad has a first surface in contact with the forming screen and an opposite second surface. A moving transfer surface is provided adjacent the second surface of the pad and is moved in a direction which substantially corresponds to the movement of the pad and at a velocity which is at least as great as the tangential velocity of the forming screen. The transfer surface is engaged with the second surface of the pad and the pad is transferred to the transfer surface. During the transfer of the pad, a trailing edge of the nob exerts a compressive force on the pad wherein the compressive force includes a component vector which is directed towards the transfer surface.

In some embodiments of the method, the velocity of the transfer surface may be 101, 102, 103, or greater percentage of the tangential velocity of the forming screen at the transfer location.

In other embodiments of the method, the transfer surface may be either a flat surface or a substantially cylindrical surface. In those embodiments wherein the transfer surface is a substantially cylindrical surface, the forming screen may have a radius which less than, substantially equivalent to, or greater than the transfer surface radius. When the forming screen has a larger radius, the forming screen radius may be greater than twice or three times the magnitude of the transfer surface radius.

A variety of differently shaped nobs may be used with the methods of the present invention. The nobs may have sidewalls which incline inwardly by about  $5^\circ$  to form an angle of approximately  $85^\circ$  with the forming screen. Such nobs may also have a shape which defines a frustum. A plurality of nobs may be used on the forming screen. The nobs may also be reattachable to the screen as, for example, by using threaded fasteners to secure the nobs to the forming screen. The use of reattachable nobs allows one or more of the nobs present on the forming screen to be exchanged for a different nob in a relatively convenient manner.

The apparatus and method of the present invention provide numerous advantages. The configuration and relative motion of the forming screen and transfer surface of the apparatus and method allow the trailing edge of the nob to exert a compressive force on the fluff pad which includes a component vector directed towards the transfer surface. That portion of the compressive force which is directed towards the transfer surface assists in the transfer of the pad to the transfer surface.

Furthermore, by having the trailing edge of the nob exert a compressive force on the pad, the leading edge of the nob will not exert a compressive force on the pad. If the leading edge of the nob were to exert a compressive force on the pad, there would be a

significant possibility of the nob damaging or removing the pad material adjacent the leading edge of the nob. In contrast, the apparatus and methods of the present invention create an aperture with a relatively cleanly defined perimeter.

5 The apparatus and methods of the present invention also provide for the efficient manufacture of apertured pads. No post-formation cutting or calendering operation is required to form apertures in the pads of the present invention. Furthermore, the elimination of the post-formation cutting or calendering operation also eliminates the scrap and additional handling associated with such a post-formation aperturing process.

10 Another advantage of the present invention is that it may be implemented using reattachable nobs. When reattachable nobs are used, they may be easily exchanged for differently configured nobs. This ability allows the aperture size and geometry to be easily adjusted to optimize the performance of the pad.

#### Brief Description of the Drawings

15

The invention will be more fully understood and further advantages will become apparent when reference is made to the following detailed description of the invention and the accompanying drawings, in which:

20 Figure 1 is a partial side view of an apparatus in accordance with the present invention;

Figure 2 is a partial side view of the apparatus of Figure 1 with the operator side wall removed from the transfer roll;

Figure 3 is a top view of an apertured pad;

25 Figure 4 is a side view of a forming drum and transfer roll wherein a nob on the transfer roll is located at the normal line which intersects the centers of both the forming drum and transfer roll;

Figure 5 is a side view of the apparatus of Figure 4 wherein the forming drum has rotated 0.75°;

30 Figure 6 is a side view of the apparatus of Figure 4 wherein the forming drum has rotated 1.50°;

Figure 7 is a side view of the apparatus of Figure 4 wherein the forming drum has rotated 2.25°;

Figure 8 is a side view of the apparatus of Figure 4 wherein the forming drum has rotated 3.00°;

Figure 9 is a side view of the apparatus of Figure 4 wherein the forming drum has rotated 4.50°;

Figure 10 is a side view of the apparatus of Figure 4 wherein the forming drum has rotated 5.25°;

5        Figure 11 is a side view of the apparatus of Figure 4 wherein the forming drum has rotated 6.00°;

Figure 12 is a side view of the apparatus of Figure 4 wherein the forming drum has rotated 1.5° and which illustrates the compressive forces exerted by the nob;

10       Figure 13 is a side view of the apparatus of Figure 4 wherein the forming drum has rotated 3.0° and which illustrates the compressive forces exerted by the nob;

Figure 14 is a side view of the apparatus of Figure 4 wherein the forming drum has rotated 4.5° and which illustrates the compressive forces exerted by the nob;

15       Figure 15 is a side view of a forming drum and a flat conveyor wherein a nob on the forming drum has rotated 4° beyond a normal line located at the point where the forming drum is closest to the conveyor;

Figure 16 is a side view of the apparatus of Figure 15 wherein the forming nob has rotated to a point 6° beyond the normal line;

Figure 17 is a side view of the apparatus of Figure 15 wherein the forming nob has rotated to a point 8° beyond the normal line;

20       Figure 18 is a side view of a nob; and

Figure 19 is a top view of a forming screen and a plurality of nobs.

Corresponding reference characters indicate corresponding parts throughout the several views. The disclosed embodiments are set forth to illustrate and exemplify the invention. The disclosed embodiments are not intended to be an exhaustive illustration of  
25       the invention or to be construed as limiting the scope of the invention to the precise forms disclosed.

#### Detailed Description of the Invention

30       An apparatus for forming an apertured pad is illustrated in Figure 1. A portion of cylindrical forming drum 20 is shown in Figure 1. A forming screen 22 defines the cylindrical surface of the forming drum 20. The forming screen 22 has openings therein which allow the passage of process air but which are small enough to prevent the passage of the material used to form the pad 24. The forming screen 22 also includes

nobs 50 which both form apertures 52 within the pad 24 and assist in the release of the pad 24 from the forming drum 20. The nobs 50 are discussed in greater detail below.

The pad 24 is formed by depositing material on the forming screen within the forming chamber 26 in an air laying process. A variety of forming chambers are known in the art and provide a source of material adjacent the forming screen 22. A vacuum source operatively associated with the forming drum 20 removes air from the forming chamber 26 through the forming screen 22 and thereby deposits the material on the forming screen 22.

A wide variety of materials may be used with the present invention to form apertured pad 24. Oftentimes, pads 24 are used in consumer products intended for absorbing liquids or bodily excretions and the materials used to form such pads will generally include at least some absorbent materials. Such pads are often formed by a mixture of hydrophilic fibers and superabsorbent materials. Materials which may be used to form pad 24 include cellulosic pulp, cotton, rayon, and other natural or synthetic fibers. Superabsorbent materials may be mixed with these materials to enhance the absorbency of the pad. A fluff material derived from wood pulp is commonly used to form absorbent pads, and such fluff material may be employed with the apparatus illustrated in Figures 1 and 2. The detailed description which is presented herein discusses the present invention in terms of a pad 24 formed with such fluff material but alternative materials may also be employed with the present invention.

Prior to entering the forming chamber 26, compressed wood pulp may be pulverized in a hammermill or other fiberizing equipment to produce the fluff material. The use of hammermills and similar fiberizing equipment is well known in the art. The fluff material is then conveyed from the hammermill to the forming chamber 26. The fluff may also have additional materials added thereto, such as superabsorbent materials, either prior or subsequent to depositing the fluff material on the forming screen 22.

A scarfing unit 28 is not required, but may be advantageously positioned after the forming chamber 26 to remove excess fluff from the pad 24. The scarfing unit 28 includes a pin scarfing roll 30 and a removal air duct 32. The removal air duct 32 may be advantageously employed to recycle the removed material. For example, the duct 32 may transport the removed material to the hammermill or forming chamber 26 where the removed material may be reintroduced into the manufacturing process. Alternatively, the duct 32 may transport the material to a temporary storage chamber prior to reintroducing the material into the manufacturing process or be employed as a component in an alternative recycling or disposal method.



After removal of the excess fluff material, the pad 24 is conveyed from the forming drum 20 to a transfer surface 34. The transfer surface 34 may be formed by a cylindrical transfer roll 36 as shown in Figures 1 and 2. As shown in Figures 15-17 and discussed below, the transfer surface 34 may also be formed by a flat conveyor 38.

5 The forming drum 20 utilizes a vacuum source to deposit the fluff material on the forming screen 22 in the area of the forming chamber 26. In the transfer area 40 where the pad 24 is transferred from the forming drum 20 to the transfer surface 34, the forming drum 20 does not exert a vacuum. A pad blow-off air knife 42 is located near the transfer area 40. Both the lack of a forming drum vacuum and the air knife 42 assist in the  
10 transfer of the pad 24 to the transfer surface 34 in the transfer area 40.

In the illustrated apparatus, the cylindrical transfer roll 36 is a vacuum turn roll. The transfer surface 34 of the transfer roll 36 is a perforated surface and a vacuum source 43 is operatively associated with the transfer roll 36 whereby the transfer surface 34 pulls a vacuum at the transfer area 40. The use of a vacuum within the transfer roll 36  
15 attracts the pad 24 to the transfer surface 34 and thereby assists in the transfer of the pad 24 to the transfer surface 34. A second air knife 44 is located within the transfer roll 36 to disengage the pad from the transfer roll 36. The transfer surface 34 does not exert a vacuum on the pad 24 in the area of the air knife 44.

In the apparatus illustrated in Figures 1 and 2, the pad 24 is deposited on a first  
20 tissue 46 as it leaves the vacuum area of the transfer roll 36 and is disengaged from the transfer roll 36. A second tissue 48 is subsequently deposited on the opposite surface of the pad 24. The tissues 46, 48 help to maintain the integrity of the pad 24 as it is later assembled into a product and placed in use. The use of such tissue layers with an absorbent pad is well known in the art. The use of such tissues 46, 48, however, is not  
25 required and the pad 24 may be assembled into a product without the use of such tissue layers. Alternative substrates, such as a layer of polymeric meltblown material, may also be used to enhance the integrity or cohesion of the pad 24.

It is also known to place a tissue layer on a forming roll and form a fluff pad directly on the tissue layer. When employing nobs 50 on a forming screen 22 in accordance with  
30 the present invention, however, a tissue layer is preferably not used on the forming screen. Such a tissue layer would be difficult to conform to the surface of both the forming screen 22 and the nobs 50 and the apertures 52 formed by the nobs 50 would most likely be deformed by the presence of such a tissue layer.

Following the placement of the tissues 46, 48 on opposite sides of the pad 24, the  
35 pad 24 is debulked. The pad 24 is compressed between two nip rolls to debulk the pad 24. Debulking the pad 24 reduces the thickness of the pad 24 and it may also slightly

elongate the apertures 52 formed in the pad 24. The illustrated apparatus forms a continuous fluff pad which must be cut into individual pads in the manufacture of absorbent products. The outer lateral perimeter of the pad 24 illustrated in Figure 3 may be defined by the outer lateral perimeter of the forming screen or by subsequently cutting the pad 24. A jet of water ejected at a high pressure and velocity or a die cutting operation may be used to efficiently cut the pad 24 to define its outer perimeter. It is also possible to deposit discrete individual pads on the forming screen 22 by segregating different portions of the forming screen 22 in a manner which is known in the art.

The apertures 52 are best seen in Figure 3. In the illustrated embodiment, the apertures 52 extend through the entire thickness of the pad 24. It is also possible for the apertures 52 to extend only partially through the thickness of the pad 24.

The apertures 52 are formed by the nobs 50 located on the forming screen 22. Although not visible in Figures 1-2, nobs 50 are illustrated in Figures 4-19. The nobs 50 form an appendage or protusion on the forming screen 22. When the pad 24 is removed from the forming screen 22, the pad 24 has an aperture 52 or void space at the location where the pad 24 circumscribed the nob 50. By forming the apertures 52 in this manner, a subsequent cutting or calendering process is not required to form the apertures 52.

In the apparatus and method illustrated in Figures 1 and 2, the scarfing unit 28 is positioned to remove all of the fluff material which is disposed outwardly of the distal end 60 of the nob 50. The scarfing unit 28 thereby causes the nobs 50 to intersect the pad surface 25 disposed opposite the forming screen 22. The apertures 52 formed by the apparatus and method illustrated in Figures 1 and 2 therefore extend through the entire thickness of pad 24.

In alternative embodiments of the present invention, the apertures 52 formed in the surface 23 of the pad in contact with the forming screen 22 may not extend through the entire thickness of the pad 24. For example, if the configuration of the nobs 50 and of the scarfing unit 28 allowed the fluff material to not only circumscribe but also cover the distal end 60 of the nobs 50 when the fluff material was deposited on the forming screen, the apertures 52 would extend only partially through the thickness of the pad 24 and thereby take the form of a recess with an opening, i.e., aperture 52, in only one surface of the pad 24.

The nobs 50 may be formed out of a wide variety of different materials. For example, the nobs 50 may be formed out of plastic or metal materials. Metallic nobs are advantageous because they are durable and have a relatively low coefficient of friction. An aluminum nob provided with a Teflon (i.e., polytetrafluorethylene) release coating can be used to provide a durable and low friction nob. For example, a release coating found

suitable for use with aluminum nobs was obtained under the tradename Hard Lube Coating from Pioneer Coating having offices in Green Bay, Wisconsin. A nob 50 which has both durability and a low frictional coefficient may also be obtained by placing a Teflon coating on a steel body. Teflon coatings obtained under the tradename of either Norcoat-2 or Norcoat-3 from Pioneer Coating having offices in Green Bay, Wisconsin may be used to coat steel nobs.

The nobs 50 may be advantageously attached to the forming screen 22 by using threaded fasteners 54 inserted through the forming screen 22 and engaging a threaded bore 56 in the nob 50 as schematically shown in Figure 18. Nobs may also be formed by including a protruding threaded shaft on the nob whereby the shaft may be threaded into an opening in the forming screen 22 or engaged by a nut on the opposite side of the forming screen 22.

The use of threaded fasteners 54 permit the nobs 50 to be conveniently attached, detached and reattached to the forming screen 22. When using such nobs, a first set of nobs may be relatively conveniently exchanged for a second set of nobs having a different size or geometric shape to alter the size and shape of the apertures in resulting pad. The use of threaded fasteners also permit individual nobs to be exchanged.

It is envisioned that the use of reattachable nobs on the forming screen 22 could also enable the nob positions to be reconfigured to alter the pattern of apertures 52 formed in the pad 24. The insertion of a threaded fastener through the forming screen 22, however, can damage the screen.

Nobs 50 may also be welded or otherwise permanently affixed to the forming screen 22. Less substantial materials and attachment methods can also be used to form and attach the nobs 50. For example, foam rubber nobs 50 adhered to a forming screen 22 with double sided tape have been successfully employed for limited production runs and may be removed or reconfigured without damaging the forming screen 22.

Figure 19 illustrates a forming screen 22 with a plurality of nobs 50 attached thereto in a first pattern. Also shown in Figure 19 are dashed lines 21 which designate the position where the outer lateral edges of the fluff pad 24 will be located after the fluff material has been deposited on the forming screen 22. As can be seen from Figure 19, the nobs 50 lie within the interior region of the forming screen whereby the nobs 50 will be completely circumscribed by the fluff material deposited on the forming screen 22. In other words, if a projection similar to a nob 50 was positioned along the lateral edge of the forming screen 22 whereby it defined a portion of the lateral perimeter of the fluff pad 24 (and corresponded with dotted line 21) it would not be completely circumscribed or encircled by the deposited fluff material and would not define an aperture within the pad.

The illustrated nobs 50 do not include perforations or apertures on either the sidewalls or distal end of the nob 50 and, thus, process air is not pulled directly through the illustrated nobs 50. It would be possible, however, for the nobs to include such openings on the sidewall surface 58 to allow the process air to be removed therethrough in addition to the remainder of the forming screen 22. If the apertures 52 did not extend completely through the thickness of the pad 24, it might be desirable for the distal end 60 of the nobs to include openings or for both the sidewall surface 58 and distal end 60 to include openings.

When nobs 50 without openings are employed on a forming screen 22, the total area of the forming surface which includes openings is reduced. For the pad 24 illustrated in Figure 3 which is intended for use in a diaper, there are 32 apertures and the surface area of the apertures/nobs is approximately 15 percent of the total forming surface/pad surface area. An alternative configuration of nobs 50 which result in a pad similar to that shown in Figure 3 but with only 16 apertures may also be used to produce an absorbent pad well-suited for use in a diaper.

Advantageously, the nob surface area may be between about 7 to about 15 percent, about 5 to about 25 percent, or less than about 50 percent of the total forming surface area. As used herein, the nob surface area is the cross sectional area of the nob at the base of the nob where the nob is attached to the forming screen and the total forming surface area includes the area of the forming screen on which the fluff material is deposited plus the nob surface area.

The nobs 50 may have a variety of different configurations. For example, the cross section of the nobs 50 may define a circle, oval, star, diamond, rectangle or any other geometric figure. Furthermore, the cross sectional shape of the nobs 50 may vary over the height of the nobs 50. For example, the nobs 50 may be provided with a slight taper whereby the distal end 60 of the nob 50 has an area which is less than the cross sectional area of the base of the nob at the point where the nob is attached to the forming screen 22. The inward taper of the sidewall 58 may advantageously be in the range of between 0° to about 15°. For example, sidewalls may advantageously have an inward taper of approximately 5° or 7°.

Alternatively, the sidewall surfaces 58 of the nob 50 may be perpendicular to the forming screen 22, pitched slightly outward, or vary over the perimeter or height of the nob 50. For example, a nob 50 could have a leading edge 68 which is perpendicular to the forming screen and a trailing edge 66 which is pitched slightly inward and thus have a pitch which varies over the perimeter of the nob 50. A nob 50 which is perpendicular near

its base (*i.e.*, has a 0° taper) but tapers inwardly near its distal end would have a pitch which varies over the height of the nob 50. Thus, the nobs 50 may take a variety of different shapes. The configuration of the nobs 50, however, must account for the interaction of the nob 50 and the pad 24 during the release of the pad 24 from the forming screen 22 which is described in greater detail below.

The nobs illustrated in Figures 4-18 have circular cross sections having a diameter of 1.91 cm (0.75 inch) at the base of the nob, a height of either 1.27 cm or 1.59 cm (0.5 or 0.625 inch) and a slight inward taper. As best seen in Figure 18, the sidewall 58 has an inward inclination, illustrated by angle 62, of about 5° whereby the angle formed between the inward inclining sidewall 58 and the forming screen 22 is about 85°. Thus, the nob illustrated in Figure 18 is a frustum (*i.e.*, it defines a truncated cone).

For pads 24 intended for use with conventional absorbent products, the diameter or longest lateral dimension of the nobs 50 may be advantageously varied from between about 0.95 cm (0.375 inch) to about 5.08 cm (2 inches). The pattern formed by the nobs 50 on the forming screen 22 may be varied significantly. It is generally advantageous, however, to maintain a distance between each nob 50 which is at least as great as the greatest of the nob diameter (or longest lateral dimension of the nob 50) or the height of the nob 50.

An advantageous feature of the nobs 50 of the present invention is their ability to assist in the transfer of the pad 24 from the forming screen 22 to the transfer surface 34. This aspect of the nobs 50 is schematically illustrated in Figures 4-17.

Figures 4-11 and 12-14 illustrate the transfer of an apertured pad 24 from a cylindrical forming drum 20 to a cylindrical transfer roll 36. For purposes of clarity, a single nob 50 is illustrated in Figures 4-11 as it rotates and progressively releases the apertured pad 24. A normal line 64 which connects the centers of both the forming drum 20 and the transfer roll 36 is shown in Figures 4-11 and provides a common reference location in each of these Figures. The forming screen 22 and transfer surface 34 are respectively rotated about the centers of the forming drum 20 and transfer roll 36 in opposite rotational directions whereby the forming screen 22 and transfer surface 34 have a common direction of linear or tangential movement where they intersect the normal line 64. Thus, transfer surface 34 is moving in a direction which substantially corresponds to the movement of the pad 24 in the area near the normal line 64.

The point at which the forming screen 22 and transfer roll 36 are nearest one another lies along the normal line 64. In the transfer area near line 64, the fluff pad 24 has a first surface 23 in contact with the forming screen 22 and the moveable transfer

surface 34 is positioned adjacent the opposite second surface 25 of the pad 24. At the point where the forming screen 22 and transfer surface 34 are closest, i.e., at their intersection with normal line 64, the forming screen 22 has a first tangential velocity (oriented perpendicular to the normal line 64) and the transfer surface has a second tangential velocity (oriented perpendicular to the normal line 64). The transfer surface 34 is engaged with the second surface 25 of the pad 24 at or near the normal line 64 in the transfer area 40.

A vacuum source 43 operatively associated with the transfer roll 36 attracts the pad 24 to the transfer surface 34. As the pad 24 moves with the transfer surface 34 it is released from contact with both the forming screen 22 and the nob 50. Figures 4-11 progressively illustrate this release of the pad 24 wherein the forming screen 22 is generally cylindrical and has a diameter which is greater than three times the magnitude of the diameter of the transfer surface 34 which is also generally cylindrical. Forming screens having a diameter of approximately 154.4 cm (60.8 inches) may be advantageously used with transfer surfaces 34 having a diameter of approximately 42.4 cm (16.7 inches) to provide a forming drum diameter/transfer surface diameter ratio of 3.6.

Advantageous configurations may also be obtained by utilizing a forming screen 22 having a radius which is twice or three times as great as the radius of the transfer surface 34. Alternative embodiments may also employ forming screens 22 which have a radius which is approximately equivalent to or smaller than the radius of the transfer surface 34. For example, the use of a flat transfer surface 34 can be considered the use of a transfer surface 34 having an infinite radius.

Figures 4-14 illustrate a forming drum 20 having a diameter of 154.4 cm and a transfer surface with a diameter of 42.4 cm; wherein the tangential velocity of the transfer surface 34 is equivalent to the tangential velocity of the forming screen 22; and nob 50 has a height of approximately 1.27 cm (0.5 inch).

Figure 4 illustrates a representative nob 50 when it is centered on the normal line 64. Figure 5 illustrates the point at which the nob 50 has rotated  $0.75^\circ$  (or 0.013 radians) about the center of the forming drum 20 past normal line 64. Figures 6-11 illustrate the nob 50 after it has respectively rotated  $1.5^\circ$ ,  $2.25^\circ$ ,  $3^\circ$ ,  $4.5^\circ$ ,  $5.25^\circ$  and  $6^\circ$  past normal line 64.

As can be seen in Figures 4-11, the trailing edge 66 of the nob 50 impinges upon the fluff pad 24 during the release of the pad 24 from the nob 50 and forming screen 22. That portion of the trailing edge of the nob 50 which impinges upon the pad 24 exerts a

compressive force on the pad 24 and forms a thrust surface 65. The thrust surface 65 is located on the trailing edge 66 instead of the leading edge 68 of the nob 50 because of the relative tangential velocities of the forming screen 22 and transfer surface 34 in the transfer area 40 and the spatial configuration of the forming screen 22, nob 50 and transfer surface 34 in the transfer area 40.

The leading edge 68 of the nob 50 would impinge upon the pad 25 and exert compressive forces thereon if the transfer surface 34 had a relatively low velocity in comparison to the velocity of the forming screen 22. The spatial configuration of the forming screen 22, nob 50 and transfer surface 34 in the transfer area 40 will determine the precise point at which a relative increase in the velocity of the transfer surface 34 causes the trailing edge 66 of the nob 50 to exert a compressive force on the pad 24 instead of the leading edge 68 of the nob 50.

When employing a forming screen 22 and transfer surface 34 which are both generally cylindrical and wherein the radius of the transfer surface 34 is less than the radius of the forming screen 22, the trailing edge 66 of the nob 50 will generally impinge upon the fluff pad 24 when the transfer surface 34 has a tangential velocity which is at least as great as the tangential velocity of the forming screen in the transfer area. Further relative increases in the speed of the transfer surface 34 to 101, 102 or 103 percent of the velocity of the forming screen 22 in the transfer area 40 may also be advantageous. An excessive difference in the relative velocities of the transfer surface 34 and the forming screen 22, however, can cause damage to the pad 24 such as the stretching and cracking of the pad 24 during the release and transfer process.

In the embodiment illustrated in Figure 1, the apparatus may be advantageously operated whereby the forming screen 22 has a tangential velocity of approximately 304.8 m/min (1,000 ft/min) and the transfer surface 34 has an approximately equivalent tangential velocity. Conventional forming screens are often operated at rates which produce tangential velocities within the range of approximately 91.4 m/min (300 ft/min) to 304.8 m/min (1,000 ft/min). The present invention may advantageously utilize a forming screen 22 operating within this velocity range but is not limited to this range of velocities.

Figures 12-14 are enlargements of the nob 50 in the same rotational positions shown respectively in Figures 6, 8 and 9. The compressive pressure exerted by the thrust surface 65 on the pad 24 can be denoted by a force vector 70 which represents the direction and magnitude of the total compressive pressure exerted by the thrust surface 65 located on the trailing edge 66 of the nob 50 against the pad 24. The actual compressive force 70 exerted by the thrust surface 65 will vary in magnitude as the nob

50 is withdrawn from the pad 24. That portion of the trailing edge 66 of the nob 50 which forms the thrust surface 65 will also change as the nob 50 is withdrawn from the pad 24.

The actual magnitude of the compressive force 70 will be dependent upon a number of variables, including not only the spatial configuration of the forming screen 22, nob 50 and transfer surface 34, but also the materials used to form the nob 50 and the pad 24. For example, the modulus of elasticity and Poisson's ratio of both the nob 50 and the pad 24 will affect the magnitude of the compressive force 70. As a general rule, denser pads will result in the nob exerting larger compressive forces. There will also be frictional forces existing between the nob 50 and the pad 24 which, when added to the compressive force 70, will result in a net force having a slightly different magnitude and orientation than the compressive force 70.

With regard to the spatial configuration of the apparatus, a taller nob will generally produce larger compressive forces than a shorter nob and a smaller diameter forming screen will generally produce larger compressive forces than a larger diameter forming screen. The determination of an exact magnitude for compressive force 70 can be quite complex. For the purposes of Figures 12-14, however, the magnitude of the compressive force 70 has been simplified and is represented at a constant value of 2.00 units of force.

The orientation of the compressive force 70 is more readily determined than the magnitude of the force 70. The direction of the compressive force 70 is primarily determined by the spatial configuration of the forming screen 22, nob 50 and transfer surface 34 and the relative motion of these apparatus components which determines the area and depth to which the nob 50 impinges upon the pad 24.

A variable which may affect the net force exerted by the nob 50 on the pad 24 is the frictional resistance between the pad 24 and the nob 50. Compressive force vectors 70 are illustrated in the Figures of the present application rather than the net force vectors. The orientation of the illustrated vectors 70 would substantially correspond to the orientation of the net force exerted by the nob 50 upon the pad 24 if the interface between the nob 50 and pad 24 is assumed to be frictionless. Such an assumption is reasonable for nobs 50 such as those illustrated in the Figures which have a friction-reducing coating and a slight-inward taper.

The compressive force 70 can be defined by two component vectors which are illustrated in Figures 12-14. One of the component vectors 72 is directed towards the transfer surface 34 and is normal to the transfer surface 34 at the location nearest the point on the thrust surface 65 corresponding to the origin of the compressive force 70. The second component vector 74 is at a right angle to the first component vector 72 and is oriented opposite to the direction of travel of the pad 24. When added together, vectors



72 and 74 are equivalent to compressive force vector 70. Because the first component vector 72 has an orientation which is normal to the transfer surface 34, it assists in the transfer of the pad 24 to the transfer surface 34.

The orientation of the compressive force 70 is determined, in part, by the shape and configuration of the nob 50. As the fluff is air-laid on the forming screen 22, it is subjected to a vacuum and thereby strongly attracted towards the forming screen 22. As the forming screen 22 rotates towards the transfer area 40, the fluff forming pad 24 is no longer subjected to a vacuum and expands slightly outwardly from the forming screen 22. During this expansion of the fluff material, the pad 24 also expands laterally to engage the sidewalls 58 of the nobs 50, if the fluff material did not already so engage the sidewalls 58 of the nobs 50. (The front portion of the sidewall 58 forms the leading edge 68 of the nob 50 while the rear portion of the sidewall 58 forms the trailing edge 66 of the nob 50.)

Due to this expansion of the fluff material, beveling or undercutting the nob 50 would result in the fluff material expanding into the undercut space between the forming screen 22 and nob 50 when the vacuum is no longer attracting the fluff against the forming screen 22. Depending upon the angle of such a bevel or outward taper, some of the fluff material could become entrapped between the nob 50 and forming screen 22 during the release of the pad 24 and cause damage to the pad 24.

For these same reasons, the release of the pad 24 can be improved by providing a slight inward taper to the nob 50 whereby the nob 50 has a smaller cross sectional area at its distal end than at its base. The nobs 50 may advantageously have sidewalls 58 which have an inward inclination of about 5° or greater to aid in the release of the pad. By utilizing sidewalls 58 having an inclination which is approximately 5°, the apertures 52 formed by the nob 50 will have interior surfaces which do not diverge significantly from a perpendicular orientation to the outer surfaces of the pad 24 and still facilitate the release of the pad 24 as demonstrated in Figures 12-14.

As shown in Figure 12 when the nob 50 has rotated 1.5° past the normal line 64, the first vector component 72 of the compressive force 70 comprises a relatively small portion of the total compressive force 70. In the illustrated configuration, and examining only the compressive force and not any frictional forces, the first vector component 72 has a magnitude of 0.33 units of force for every 2.0 units of total compressive force 70. Figure 13 illustrates the point at which the nob 50 has rotated 3° past the normal line 64. At this point, the first vector component 72 has a magnitude of 0.57 units for every 2.0 units of total compressive force 70. Figure 14 illustrates the point at which the nob 50 has rotated

4.5° past the normal line 64. At this point, the first vector component 72 has a magnitude of 0.79 units for every 2.0 units of total compressive force 70.

Thus, in the configuration illustrated in Figures 12-14, the percentage of the total compressive force 70 which is directed normal to the transfer surface 34 increases as the nob 50 releases the pad 24. It can also be seen from Figures 12-14 that the total area of the thrust surface 65 progressively decreases as the nob 50 releases the pad 24 and that the extent of impingement by the thrust surface 65 upon the pad 24 progressively increases as the pad 24 is released.

Figures 15-17 illustrate the transfer of an apertured pad from a cylindrical forming screen 22 to a flat conveyor 38. The transfer surface 34 of the flat conveyor 38 may be operatively associated with a vacuum source whereby a vacuum is used to attract the pad 24 to the flat conveyor 38 and assist the transfer.

The transfer of the pad 24 to a flat transfer surface 34 can also be assisted by the trailing edge 68 of the nob 50 imparting a compressive force on the pad 34 in the same manner as that described above for the transfer of a pad 24 to a cylindrical transfer surface 34. When the transfer is to a flat transfer surface 34, however, the relative velocity of the transfer surface 34 will have to be increased relative to the velocity of the forming screen to ensure that it is the trailing 66, rather than the leading 68 edge of the nob 50 which impinges upon the pad 24.

The forming screen 22 and nob 50 illustrated in Figures 15-17 are similar to those illustrated in Figures 12-14. Figures 15-17, however, depict a flat transfer surface 34 wherein the transfer surface 34 of the flat conveyor 38 has a velocity which is 103 percent of the velocity of the forming screen 22. Arrow 39 indicates the direction of travel of the flat conveyor 38.

For the apparatus illustrated in Figures 15-17, when the velocity of the flat transfer surface 34 is equivalent to the velocity of the forming screen 22, the leading edge 68 of the nob 50 will impinge upon the pad 34. When the flat transfer surface 34 has a velocity which is 101 percent of the velocity of the forming screen 22, the nob 50 will impinge upon the pad 34 with both the leading edge 68 and trailing edge 66 and at approximately equal magnitudes at different points during the release process. When the velocity of the flat transfer surface 34 has been relatively increased to 102 percent of the velocity of the forming screen 22, however, it will be the trailing edge 66 of the nob 50 which will primarily impinge upon the pad 34 and the nob 50 will thereby assist in the transfer of the pad 24 to the flat transfer surface 34. If the velocity of the flat transfer surface 34 exceeds 103 percent of the velocity of the forming screen surface, *i.e.*, it has a draw of more than 103

percent, a pad 24 formed primarily out of cellulosic fluff material may be damaged by stretching or cracking.

For the embodiment illustrated in Figures 15-17, when the forming screen 22 has a velocity of approximately 304.8 m/min (1,000 ft/min) and the flat transfer surface 34 has a velocity of approximately 102 to 103 percent of the forming screen velocity, the trailing edge 66 of the nob 50 will impinge upon the pad 24 and a pad 24 formed out of cellulosic fluff material will be unlikely to experience stretching or cracking due to the differential in velocities.

It is noted that a particular relative difference in the tangential velocity of the forming screen 22 and the transfer surface 34 corresponds to a particular relative difference in the tangential linear advancement of the forming screen 22 and transfer surface 34 regardless of the absolute velocity of the forming screen 22 and transfer surface 34. For example, if the transfer surface 34 has a velocity of 101 percent of the forming screen 22, the transfer surface 34 will advance 101 cm for every 100 cm the forming screen 22 advances, regardless of their absolute velocities.

While this invention has been described in detail, it will be readily apparent to a person of ordinary skill in the art that various changes and modifications can be made without departing from the spirit and general principles of the invention. All of such changes and modifications are contemplated as being within the scope of the present invention as defined by the subjoined claims. Furthermore, this application is intended to cover such departures from the present disclosure as come within known or customary practice in the art.

What is claimed is:

1. A method of manufacturing a pad, said method including:  
providing a forming screen with at least one outwardly projecting nob;  
rotating said forming screen whereby said forming screen has a first tangential velocity;  
5 forming the pad on said forming screen wherein the pad completely encircles said at least one nob, the pad having a first surface disposed in contact with said forming screen and a second surface disposed opposite the first surface;  
providing a moving transfer surface adjacent the second surface of the pad, said transfer surface moving in a direction substantially corresponding to the movement of the  
10 adjacent second surface, said transfer surface moving at a second velocity which is at least as great as said first velocity;  
engaging said transfer surface with the adjacent second surface; and  
transferring the pad to said transfer surface wherein a trailing edge of said nob exerts a compressive force on the pad, said compressive force including a component  
15 vector directed towards said transfer surface.
2. The method of claim 1 wherein the second surface of the pad is intersected by said nob.
3. The method of claim 1 wherein said transfer surface is a flat surface.
4. The method of claim 3 wherein said second velocity is greater than said first velocity.
5. The method of claim 3 wherein said second velocity is at least about 102 percent of said first velocity.
6. The method of claim 3 wherein said second velocity is at least about 103 percent of said first velocity.
7. The method of claim 1 wherein said transfer surface is a cylindrical surface.
8. The method of claim 1 wherein said forming screen includes a plurality of outwardly projecting nobs.

9. The method of claim 1 wherein said at least one nob is reattachably secured to said forming screen.

10. The method of claim 9 wherein said at least one nob is threadingly attachable.

11. The method of claim 1 wherein said at least one nob has a distal end and side walls extending from said forming screen to said distal end, said nob having a first cross sectional area at said forming screen and a second cross sectional area at said distal end, at least a portion of said side walls having an inward inclination of at least about 5 degrees.

12. The method of claim 11 wherein said at least one nob is a frustum.

13. The method of claim 1 wherein said transferring step further includes using a vacuum to attract the pad to the transfer surface.

14. A method of manufacturing a pad, said method including:

providing a forming screen, said forming screen defining a first cylindrical surface with a first radius and having at least one outwardly projecting nob;

5 rotating said forming screen whereby said forming screen has a first tangential velocity;

forming the pad on said forming screen whereby the pad completely encircles said at least one nob, the pad having a first surface disposed in contact with said forming screen and a second surface disposed opposite the first surface;

10 providing a rotatable transfer surface adjacent the second surface of the pad, said transfer surface defining a second cylindrical surface with a second radius;

engaging said transfer surface with the second surface of the pad at a second tangential velocity which is at least as great as said first velocity, said forming screen and said transfer surface having opposite rotational directions; and

15 transferring the pad to said transfer surface wherein a trailing edge of said nob exerts a compressive force on the pad, said compressive force including a component vector directed towards said transfer surface.

15. The method of claim 14 wherein the second surface of the pad is intersected by said nob.

16. The method of claim 14 wherein said second velocity is greater than said first velocity.

17. The method of claim 14 wherein said second velocity is at least about 101 percent of said first velocity.

18. The method of claim 14 wherein said second velocity is at least about 102 percent of said first velocity.

19. The method of claim 14 wherein said second velocity is at least about 103 percent of said first velocity.

20. The method of claim 14 wherein said at least one nob has a distal end and side walls extending from said forming screen to said distal end, said nob having a first cross sectional area at said forming screen and a second cross sectional area at said distal end, said first cross sectional area being greater than said second cross sectional area, at least a portion of said side walls having an inward inclination of least about 5 degrees.

21. The method of claim 20 wherein said at least one nob is a frustum.

22. The method of claim 14 wherein said forming screen has a plurality of outwardly projecting nobs.

23. The method of claim 14 wherein said at least one nob is reattachably secured to said forming screen.

24. The method of claim 23 wherein said at least one nob is threadingly attachable.

25. The method of claim 14 wherein said first radius is substantially equivalent to said second radius.

26. The method of claim 14 wherein said first radius is larger than said second radius.

27. The method of claim 14 wherein said transferring step further includes using a vacuum to attract the pad to the transfer surface.

28. An apparatus for manufacturing a pad, said apparatus comprising:

a rotatable forming screen, said forming screen having a generally cylindrical surface and at least one outwardly projecting nob, said at least one outwardly projecting nob interiorly positioned on said forming screen whereby said forming screen circumscribes said nob, said forming screen being rotatable at a rate defining a first tangential velocity;

a material source positioned adjacent said forming screen whereby a material layer is depositable on said forming screen and said at least one nob is circumscribable by the material layer, the material layer thereby forming the pad and having a first surface disposed in contact with said forming screen and a second surface disposed opposite said first layer;

a moveable transfer surface, said transfer surface being engageable with the second surface of the material layer, said transfer surface being moveable in a direction substantially corresponding to the movement of the engageable material layer and at a second velocity, said second velocity being at least as great as said first velocity;

a means for attracting the material layer to said transfer surface; and

a thrust surface disposed on a trailing edge of said at least one nob, said thrust surface imparting a compressive force on the engageable material layer as said forming screen and said transfer surface respectively move at said first and second velocities, said compressive force including a component vector directed towards said transfer surface.

29. The apparatus of claim 28 wherein said transfer surface is a substantially flat surface.

30. The apparatus of claim 29 wherein said second velocity is greater than said first velocity.

31. The apparatus of claim 29 wherein said second velocity is at least about 102 percent of said first velocity.

32. The apparatus of claim 29 wherein said second velocity is at least about 103 percent of said first velocity.

33. The apparatus of claim 28 wherein said transfer surface is a substantially cylindrical surface.

34. The apparatus of claim 28 wherein said forming screen includes a plurality of outwardly projecting nobs interiorly positioned on said forming screen whereby said forming screen circumscribes each of said plurality of nobs.

35. The apparatus of claim 28 wherein said at least one nob is reattachable on said forming screen.

36. The apparatus of claim 35 further comprising a threaded fastener securing said at least one nob.

37. The apparatus of claim 28 wherein said at least one nob has a distal end and side walls extending from said forming screen to said distal end, said nob having a first cross sectional area at said forming screen and second cross sectional area at said distal end, at a portion of said side walls having an inward inclination of at least about 5 degrees.

38. The apparatus of claim 37 wherein said at least one nob is a frustum.

39. The apparatus of claim 28 further comprising a scarfing device, said scarfing device positioned to remove excess material disposed outwardly of a distal end of said at least one nob.

40. The apparatus of claim 28 wherein said means for attracting the material layer comprises a vacuum source disposed in operative communication with said transfer surface.

41. An apparatus for manufacturing a pad, said apparatus comprising:

a rotatable forming screen, said forming screen defining a first generally cylindrical surface with a first radius and having at least one outwardly projecting nob, said at least one outwardly projecting nob interiorly positioned on said forming screen whereby said forming screen circumscribes said nob, said forming screen being rotatable at a rate defining a first tangential velocity;

a material source positioned adjacent said forming screen whereby a material layer is air layable on said forming screen and said at least one nob is circumscribable by the material layer, the material layer thereby forming a pad and having a first surface disposed in contact with said forming screen and a second surface disposed opposite said first layer;



15 a rotatable transfer surface, said transfer surface defining a second generally cylindrical surface with a second radius, said transfer surface being engageable with the second surface of the material layer, said transfer surface and said forming screen having opposed rotatable directions, said transfer surface being movable at a second tangential velocity, said second velocity being greater than said first velocity;

20 a vacuum source disposed in operative communication with said transfer surface whereby said material layer is attractable to said transfer surface; and

a thrust surface disposed on a trailing edge of said at least one nob, said thrust surface imparting a compressive force on the engageable material layer as said forming screen and said transfer surface respectively move at said first and second velocities, said compressive force including a component vector directed towards said transfer surface.

42. The apparatus of claim 41 wherein said first radius is substantially equivalent to said second radius.

43. The apparatus of claim 41 wherein said first radius is larger than said second radius.

44. The apparatus of claim 41 wherein said second velocity is greater than said first velocity.

45. The apparatus of claim 41 wherein said second velocity is at least about 101 percent of said first velocity.

46. The apparatus of claim 41 wherein said second velocity is at least about 102 percent of said first velocity.

47. The apparatus of claim 41 wherein said second velocity is at least about 103 percent of said first velocity.

48. The apparatus of claim 41 wherein said forming screen includes a plurality of outwardly projecting nobs interiorly positioned on said forming screen whereby said forming screen circumscribes each of said plurality of nobs.

49. The apparatus of claim 41 wherein said at least one nob is reattachable on said forming screen.

50. The apparatus of claim 49 further comprising a threaded fastener securing said at least one nob.

51. The apparatus of claim 41 wherein said at least one nob has a distal end and side walls extending from said forming screen to said distal end, said nob having a first cross sectional area at said forming screen and second cross sectional area at said distal end, a portion of said side walls having an inward inclination of at least about 5 degrees.

52. The apparatus of claim 51 wherein said at least one nob is a frustum.

53. The apparatus of claim 41 further comprising a scarfing device, said scarfing device positioned to remove excess material disposed outwardly of a distal end of said at least one nob.




FIG. 1

2 / 7




FIG. 2






FIG. 3






FIG. 12

FIG. 13






FIG. 14



**FIG. 15**



**FIG. 16**






FIG. 17



7 / 7

**FIG. 18****FIG. 19**

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 00/07324

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 A61F13/15

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 A61F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EP0-Internal

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 4 761 258 A (ENLOE KENNETH M) 2 August 1988 (1988-08-02) figures 1,2,5	1-53
A	US 5 494 622 A (HEATH MARK G ET AL) 27 February 1996 (1996-02-27) figures 7,9	1-53

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents :

\*A\* document defining the general state of the art which is not considered to be of particular relevance

\*E\* earlier document but published on or after the international filing date

\*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

\*O\* document referring to an oral disclosure, use, exhibition or other means

\*P\* document published prior to the international filing date but later than the priority date claimed

\*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

\*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

\*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

\*8\* document member of the same patent family

Date of the actual completion of the international search

31 July 2000

Date of mailing of the international search report

11/08/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Louter, P

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 00/07324

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4761258 A	02-08-1988	AT 82597 T	15-12-1992
		AU 602301 B	04-10-1990
		AU 4001089 A	07-12-1989
		AU 590032 B	26-10-1989
		AU 6632486 A	11-06-1987
		BR 8606107 A	15-09-1987
		CA 1284010 A	14-05-1991
		DE 3687143 A	24-12-1992
		DE 3687143 T	03-06-1993
		EP 0226939 A	01-07-1987
		JP 2613735 B	28-05-1997
		JP 7119013 A	09-05-1995
		JP 2694943 B	24-12-1997
		JP 62206071 A	10-09-1987
		KR 9310349 B	16-10-1993
		MX 166011 B	16-12-1992
		ZA 8609265 A	29-07-1987
<hr/>			
US 5494622 A	27-02-1996	CA 2138680 A	13-01-1996
<hr/>			